

# PUR Adhesive 507.9

**Humidity curing single-component reaction adhesive based on polyurethane, highly resistant to water and temperature.**

**Water resistance according to DIN EN 204, D4.**

## Fields of application

- Bonding windows and doors
- Laminate bonding of wood and wood materials
- Joint bonding for exterior area
- Bonding of mineral building boards, ceramic and concrete materials and hard foams

## Advantages

- Single-component adhesive, no pot life problems
- Easy application
- Very light joint
- Low foaming

## Properties of the bond

- The thermosetting glue joint is resistant to high temperatures and achieves highest bonding strength
- Bond quality D4 according DIN EN 204 (internal testing)

## Properties of the adhesive

<b>Base:</b>	isocyanate
<b>Colour:</b>	colorless
<b>Specific gravity:</b>	approximately 1.13 g/cm <sup>3</sup>
<b>Viscosity</b>	
<b>- Brookfield RVT:</b>	3,500 ± 800 mPa s
<b>Consistency:</b>	fluid
<b>Open time</b>	
<b>(at 20°C and 50% RH):</b>	15 ± 3 minutes
<b>Identification:</b>	identification required according to EU regulations, contains 4.4 diphenyl methane diisocyanate (see our safety data sheet)
<b>Note:</b>	Intended for commercial use only.

## Application techniques

### Processing conditions:

The ideal working temperature is +20°C, the ideal moisture content of the wood 8-12 %.

Do not process below +5°C.

The adherents must be clean, dry and free from grease. Remove release agent from plastic surfaces.

### Application methods:

With spatula or hand roller from plastic squeeze bottle

### Application:

single-sided application suffices on less porous surfaces

### Application quantity:

100-200 g/m<sup>2</sup> according to the condition of the material

### Open time:

Approx. 15 minutes at approx. 20°C. This period is reduced by high room temperatures, high humidity or the supply of moisture.

### Setting:

The adhesive hardens to a water-resistant, solvent-resistant and semi-rigid adhesive film when exposed to humidity (from the air or materials being bonded).

The cross-linking process can be accelerated by means of targeted moisture supply (water spray, approx. 20 g/m<sup>2</sup>) or by higher temperatures (40°C up to max. 70°C).

### Pressing the parts:

The cross-linking process takes place when sufficient pressure is applied to ensure contact with the surfaces to be bonded.

Use silicon paper to protect from any adhesive which is squeezed out.

The necessary pressure is dependent on the kind and size of the materials; a good joint fit should be ensured. Minimum pressure for the bonding of laminated wood: **0.6 N/mm<sup>2</sup>**. The more intensive the cross-linking of the adhesive under pressure, the higher the subsequent loading ability.

## PUR Adhesive 507.9

### Press times:

The press times are dependent on temperature and moisture supply.

Guide values:

Temperature	Press Time
20°C	45 – 60 minutes
40°C	25 – 30 minutes
60°C	15 – 20 minutes

Exact times must be established for the particular application according to the conditions in question.

### Final setting time:

Subsequent processing of the bonded parts is possible after 1 – 2 hours, final strength is achieved after approximately 7 days.

### Cleaning

Clean application tools with KLEIBERIT Cleaner 820.0 toluene-free **immediately** following use.

### Packaging

#### KLEIBERIT PUR Adhesive 507.9:

metal can, 30 kg net

#### KLEIBERIT Cleaner 820.0 Toluene-free:

metal canister, 4.5 kg net

metal can, 22 kg net

Additional packaging sizes available upon request.

### Storage

KLEIBERIT PUR Adhesive 507.9 can be stored in closed air-tight containers at 20°C for approx. 9 months.

Keep in a cool and dry place and carefully protect from humidity.

Opened containers should be used up as soon as possible.

KLEIBERIT PUR Adhesive 507.9 is not frost sensitive at temperatures above -20°C.

Version KH 0912

#### Waste Disposal

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.  
Our containers are made of recyclable material.

#### Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.