

KLEIBERIT 651.0.01

UV Filler for roller application

Fields of Use

- Photosensitive UV base coat for the KLEIBERIT HotCoating[®] technology with high transparency and very good sandability.

Characteristics of 651.0.01

Base:	UV curing acrylates
Specific weight (at 20 °C):	approx. 1.19 g/cm ³
Solids:	>99 % (theoretical value)
Colour:	colorless, typical
Gloss level:	typical for the material, matt, not determined

Viscosity at delivery (at 20 °C)

8 mm DIN cup:	45 - 60 seconds
Brookfield S5V20:	3.000 - 4.000 mPa·s

Identification: See our safety data sheet

Processing

Ambient and substrate processing
temperature: 22 - 28 °C
Application with roller applicator: 10 - 55 g/m²
Application viscosity: viscosity at delivery

Stir well by machine before use.
All process relevant properties must be checked before processing.

Drying / UV-Curing

Gelling:	10 m/min
UV-Dosage*:	100 - 200 mJ/cm ² (Hg)

Curing:	10 m/min
UV-Dosage*:	700 - 1200 mJ/cm ² (Hg)

* The stated UV dosages are empirical values based on measurements with „UV-Disc A002400 (Full-UV: 250 – 410 nm)“ by UV-Technique
It is absolutely necessary to determine the processing conditions for optimal result before starting production.

These depend on the equipment technology as well as on the substrate to be coated. The final characteristics like adhesion, scratch resistance and sandability have to be monitored continuously.

Cleaning

Soiled application tools and machinery parts to be cleaned immediately with KLEIBERIT 820.0.

Packaging

KLEIBERIT 651.0.01
plastic canister, 20 kg net
IBC container, 1,000 kg net
metal pail, 25 kg net

Cleaner

KLEIBERIT 820.0
metal can, 22 kg net

Additional packaging sizes available upon request.

Storage

Shelf life in factory sealed containers (at 5 - 25 °C) is at least 12 months. Storage at high temperatures can shorten the shelf life.

Protect from light, heat and frost.

Version 16/03/2022 lz; replaces previous versions

KLEIBERIT 651.0.01

Disposal of containers and contents

Waste disposal key **080111**

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.
Our containers are made of recyclable material.

Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.