



KLEIBERIT 657.0.10

UV curing top coat for roller application, super matt

Fields of Use

 Photosensitive UV top coat for the KLEIBERIT HotCoating® technology for high scratch resistance and gloss levels of < 5 units.

Characteristics of 657.0.10

Base: UV curing acrylates

Specific weight

(at 20 °C): approx. 1.11 g/cm³

Solids: >99 % (theoretical value)

Colour: uncolored, typical

Gloss level < 60°: < 5 units

The gloss level depends on the

processing parameters.

Viscosity at delivery (at 20 °C)

6mm DIN cup: 25 - 35 seconds

Identification: Identification is required according

to EU regulations

(See our safety data sheet)

Processing

Ambient and substrate processing

temperature: 22 - 28 °C

Application with roller applicator: 25 - 30 g/m² Application viscosity: viscosity at delivery

Stir well before use.

<u>All process relevant properties must be</u> checked before processing.

Drying / UV-Curing

Precuring: excimer Curing: 10 m/min

UV-Dosage*: 800 - 1200 mJ/cm² (Hg)

* The stated UV dosages are empirical values based on measurements with "UV-Disc A002400 (Full-UV: 250 – 410 nm)" by UV-Technique It is absolutely necessary to determine the processing conditions for optimal result before staring production.

These depend on the equipment technology as well as on the substrate to be coated.

The final characteristics like adhesion, scratch resistance and sandability have to be monitored continuously.

Cleaning

Soiled application tools and machinery parts to be cleaned immediately with KLEIBERIT 820.0.

Packaging KLEIBERIT 657.0.10

metal pail, 25 kg net IBC container, 1,000 kg net

Cleaner

KLEIBERIT 820.0

metal can, 22 kg net

Additional packaging sizes available upon request.

Storage

Shelf life in factory sealed containers (at 5 - 25°C)

is at least 9 months.

Storage at high temperatures can shorten the shelf life

Recommended transport temperature -10 - 35 °C.

Protect from light, heat and frost.

Version 07/08/2019 al; replaces previous versions

Restricted to professional users



KLEIBERIT 657.0.10

Adhesive and Waste Disposal

Waste Code 080111

Our containers are made of recyclable material. Well drained containers can be

Service
Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.

Restricted to professional users

Page 2 of 2